

Supplied by: Delta Membrane Systems Ltd.

Tel. 01992 523523 Fax. 01992 523250 E-mail: info@deltamembranes.com

Technical data sheet for DELTA-THAN

Product	DELTA-THAN
Packaging / Packing	Cartridge 310ml; 12 pieces/carton; ~100cartons/pallet
Assembly	Styrol rubber, solvent based, black
Characteristics	Pasty goods, after ligation the glue is elastic and mechanical able to work under pressure
Application	For the adhesion of overlapping areas of DELTA membranes and for the connection between brickwork, concrete, wood, aluminium, steel, rigid PVC and elastic PVC, bitumen – membranes, - surfaces.
	Before bonding of PE membranes, the applicability has to be checked. Not adequate for the printed surface of DELTA-MAXX/DELTA-MAXX PLUS
Use	~ 7m/cartridge
Necessary surface tension of the underground	(-)
Period of storage	12 months unopened
storage climate	Cool and free of frost
climate of handling	+ 5° to + 40°C
open time	10 min.
Conditioning time	Diffusion-open materials 1h, Diffusion-hindering materials ~ 24h
Functional area	- 30° to + 80°C
Advice of application	Application of an about 8mm thick crawler on the underground. Make sure that you press on overlapping. Connections with brickwork etc., as a fit-up aid, have to be mechanical protect (for example with nails). Porous Undergrounds have to be primed with DELTA-THENE GRUNDANSTRICH or DELTA-PRIMER.
General advice	Underground has to be clean, dry, free of dust, grease and frost and adequately sustainable. Not adequate sustainable undergrounds, for example sandy undergrounds are able to be primed with DELTA-AGF ALLGRUNDFIX
Special advice	Please take care of sufficient air ventilation while curing.
Status	September 2008